



Face Material

weight	thickness	material
25±10%/m ² ISO 536	0.025±10%mm ISO 534	Clear Polyester

Liner

80±10%/m ² ISO 536	0.8±10%mm ISO 534	Yellow glassine treated with super calender
-------------------------------	-------------------	---

Adhesive

Permanent high-viscosity water-based acrylic pressure-sensitive adhesive for films, especially on the surface of non-polar materials such as PE, has excellent performance on a variety of materials.

Peel adhesion

Initial adhesion 14N/25mm FTM 9 st.st	20 minutes Peel adhesion value on steel at 180° 9N/25mm or tear off FTM 1 st.st	20 minutes Peel adhesion value on steel at 90° 7N/25mm or tear off FTM 2 st.st
--	---	--

Temperature

Min. Appl. Temp. 5 °C	Service Temp. -35~90°C(after 24hrs)
-----------------------	-------------------------------------

Applications

For sealing sticker, no printing coating.

The above suggestion, application, and elaboration are not intended as the guarantee of Siga. All sales of Siga products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

Provides excellent stiffness, and die-cutting properties, excellent chemical and UV resistance.

Shelf life

12 months, applicable only to the material delivered by Siga which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23±2°C and 50±5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.