



名称: **PPGF30**

牌号: **B0730**

产品简介 Product Description	主要应用 Applications
·30%玻纤增强聚丙烯 30% glass fiber reinforced PP	·注塑成型 Injection molding
·优异的热老化性能 Excellent Heat Stability	·良好的机械性能 Good mechanical properties balance

性能 Properties	测试标准 Test Method	测试条件 Test Condition	单位 Unit	典型值 Typical Values
物理性能 Physical properties				
密度 Specific Gravity	ISO 1183	23℃	g/cm ³	1.13
灰份 Ash	ISO 3451	650℃,30min	%	30
机械性能 Mechanical properties				
拉伸强度 Tensile Strength	ISO 527	50mm/min	MPa	75
弯曲模量 Flexural Modulus	ISO 178	2mm/min	MPa	5500
弯曲强度 Flexural Strength	ISO 178	2mm/min	MPa	120
简支梁缺口冲击强度 Charpy Notched Impact Strength	ISO 179-1eA	23℃	kJ/m ²	13
简支梁无缺口冲击强度 Charpy Unnotched Impact Strength	ISO 179-1eU	23℃	kJ/m ²	45
热性能 Thermal properties				
热变形温度 Heat deflection temperature	ISO 75	1.80MPa	C	135
熔点 Melting Point	DSC	—	C	164
其它性能 Other properties				
收缩率 Mold Shrinkage	internal test method	48 hours after tool	%	0.5-0.9
阻燃性 Flammability	TL1010	—	mm/min	28

说明: 以上数据是典型值, 不是保证值。根据模具设计, 例如浇口类型, 浇口分布, 浇口数量的不同, 注塑工艺和制件厚度的不同, 测试结果会有波动。不同的颜色, 测试结果也会有波动。

Note: The data above is typical value for reference, not guarantee value. The data will vary with tool design such as gate type, gate location, gate number, injection molding process and part thickness. The data will vary with different color as well.

典型加工条件 Processing Conditions	参考范围 Range	
熔体温度 Melt Temperature	210-250℃	
料筒温度 Barrel Temperature	后段, Rear	210--220℃
	中段, Center	225--235℃
	前段, Front	240--250℃
模具温度 Mold Temperature	30-50℃	
预干燥 Pre-Dry needed	90-100℃, 2h	

说明: 以上数值仅供注塑机参考使用, 可根据不同机型、不同模具以及产品要求, 对上述工艺做适当调整。

Note: The above process condition is only for reference. The actual process should be adjusted according to different type of machine, mold design and product design.