



PP TPK8003

Product introduction

PP TPK8003

良好的机械性能 Good mechanical properties

性能 Properties	测试标准 Test Method	测试条件 Test Condition	单位 Units	典型值 Typical Values
物理性能 Physical				
熔融指数 Melt Flow Rate	ISO1133	230℃, 2.16Kg	g/10min	3
密度 Specific Gravity	ISO1183	23℃	g/cm3	0.90
灰份 Ash	ISO3451	800℃,30min	%	--
机械性能 Mechanical				
屈服拉伸强度 Yield Tensile Strength	ISO527	50mm/min	MPa	22.4
屈服伸长率 Yield Elongation at Break	ISO527	50mm/min	%	8
弯曲强度 Flexural Strength	ISO178	2mm/min	MPa	--
弯曲模量 Flexural Modulus	ISO178	2mm/min	MPa	861
简支梁无缺口冲击强度 Impact Strength, IZOD non-notched	ISO179	23℃	KJ/m2	NB
		-30℃	KJ/m2	-
简支梁缺口冲击强度 Impact Strength, IZOD notched	ISO179	23℃	KJ/m2	53
		-30℃	KJ/m2	7.6
热性能 Thermal				
热变形温度 Heat Deflection Temp.	ISO75	0.45MPa	℃	95
		1.8MPa	℃	-
熔点 (Melting Point)	DSC		℃	
其他 Others				
球压硬度 Hardness	ISO2039	-	N/mm2	
收缩率 Mold Shrinkage	-	23℃		
阻燃性 Flammability	TL1010	-	mm/min	

备注 Remarks:

- 1.The data in the table is the test data of the product performance, but the value cannot be used as the guarantee value of the performance in the specific use, only for the user's reference.
- 2.The data on the flammability level in the table is not intended to reflect the degree of danger of the material under actual fire conditions.