



名称: **TPR**  
 牌号: **TPT5709**

产品简介 Product Description	主要应用 Applications
·良好的弹性 Has good flexibility	·可重复回收利用 Recyclable
·高透明 High transparency Excellent weather resistance	·良好的机械性能 Good mechanical properties balance

性能 Properties	测试标准 Test Method	测试条件 Test Condition	单位 Unit	典型值 Typical Values
<b>物理性能 Physical properties</b>				
密度 Specific Gravity	ASTM D792	23℃	g/cm <sup>3</sup>	0.868
融指 MI	ASTM D1238	160℃/5kg	g/10min	205.5
<b>机械性能 Mechanical properties</b>				
拉伸强度 Tensile Strength	ASTM D412	/	MPa	17.05
硬度 Hardness	ASTM D2240	/	Shore A	6 ~ 8
撕裂强度 Tear resistance	ASTM D624	/	kgf/cm	15.37
断裂伸长率 Elongation at break	ASTM D412	/	%	587.32
<b>其它性能 Other properties</b>				
RoHS	/	/	/	PASS

**说明:** 表中数据为本公司质量检测部门测试所得的典型值, 因为测试方法、测试环境以及一些不可控因素的存在, 可能与贵司测试结果存在些许偏差, 请根据实际情况在首次使用前进行相关测试。在使用材料之前, 请咨询拓扑新材料有限公司。

**Note:** The data in the table is the typical value obtained by the company's quality inspection department. Because of the test method, test environment and some uncontrollable factors, there may be some deviations from your company's test results. Please perform it before the first use according to the actual situation. Related tests. Prior to use the material, please consult with TOPO NEW Material Co., Ltd.

典型加工条件 Processing Conditions	参考范围 Range
熔体温度 Melt Temperature	120-140℃

**说明:** 以上数值仅供注塑机参考使用, 可根据不同机型、不同模具以及产品要求, 对上述工艺做适当调整。

**Note:** The above process condition is only for reference. The actual process should be adjusted according to different type of machine, mold design and product design.