



Face Material

weight

45±10%g/m² ISO 536

thickness

0.06±10%mm ISO 534

material

Glossy opalescent polypropylene film with special coating

Liner

58±10%g/m² ISO 536

0.055±10%mm ISO 534

White glassine treated with super calender

Adhesive

General-purpose permanent rubber-based adhesive with high viscosity and excellent processing performance. It has a good performance on the surface of glass, stainless steel, PE, PP, cartons and other materials that do not contain plasticizers.

Peel adhesion

Initial adhesion
17N/25mm FTM 9 st.st

20 minutes Peel adhesion value on steel at 180° 18N/25mm FTM 1 st.st

20 minutes Peel adhesion value on steel at 90° 9N/25mm FTM 2 st.st

Temperature

Min. Appl. Temp. 5°C

Service Temp. -35~65°C (24H after labeling)

Applications

This product has certain tensile and tearing strength which can be applied on many objects, and has high removability and water washing removal performance. This product is used to make wine bottle labels, etc. Due to the different surface energies of the objects to be applied, it is recommended to test the label on the object before use.

The above suggestion, application, and elaboration are not intended as the guarantee of Siga. All sales of Siga products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

The material has certain tear resistance and chemical corrosion resistance, and its product is widely used in industries such as washing, cosmetics, daily chemicals, food and electronic.

The above suggestion, application, and elaboration are not intended as the guarantee of Siga. All sales of Siga products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Shelf life

12 months, applicable only to the material delivered by Siga which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23±2°C and 50±5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.